

Specification Sheet: 2304 (UNS S32304)

A Duplex Stainless Steel with PREN 24

Alloy 2304 is a 23% Chromium, 4% Nickel, Molybdenum-free duplex stainless steel. The Alloy 2304 has corrosion resistance properties similar to 316L. Furthermore, its mechanical properties, i.e., yield strength, are twice those of 304L/316L austenitic grades. This allows the designer to save weight, particularly for properly designed pressure vessel applications.

The alloy is particularly suitable for applications covering the -50°C/+300°C (-58°F/572°F) temperature range. Lower temperatures may also be considered but need some restrictions, particularly for welded structures.

With its duplex microstructure and low nickel and high chromium contents, the alloy has improved stress corrosion resistance properties compared to 304L and 316L austenitic grades.

Applications

- Generally where 304L and 316L are used
- Pulp and paper industry (chip storage tanks, white and black liquor tanks, digestors)
- Caustic solutions, organic acids (SCC resistance)
- Food industry
- Pressure vessels (weight savings)
- Mining (abrasion/corrosion)

Standards

ASTM/ASME ...A240 - UNS S32304

EURONORM ...1.4362 - X2 Cr Ni 23.4

AFNOR.....Z3 CN 23.04 Az

DINW. Nr 1.4362


Corrosion Resistance

General Corrosion


Because of its high chromium content (23%) the corrosion resistance properties of 2304 are almost equivalent to those of 316L.

Localized Corrosion Resistance


The 23% chromium and 0.1% nitrogen additions explain why 2304 duplex stainless steel behaves much better than Alloy 316L when considering pitting and crevice corrosion resistance.



Corrosion resistance to stagnant sulfuric acid (0,3 mm/year)



Corrosion resistance in different organic acids





Stress Corrosion Resistance

Stress corrosion resistance test results in chloride containing aqueous solutions ((8ppm O₂) PH =7, >1000 h, applied stresses higher than the yield strength) show that Alloy 2304 outperforms 304L and 316L grades, due to its high chromium additions and low nickel contents.

This is a typical feature of duplex stainless steels. Alloy 2205 performs still better than 2304 in similar conditions.

Other Corrosion Resistance Properties

Alloy 2304 duplex stainless steel successfully passes most of the standard IC test procedures such as ASTM, A262E, and C tests. Its corrosion rate in boiling nitric acid (65%) is higher than that of grade 316L. Due to its high yield strength, the alloy performs well in abrasion/corrosion applications.



Chemical Analysis

Typical Values (Weight %)

C	Cr	Ni	Mo	N	Others
0.020	23	4	0.2	0.1	S = 0.001
PREN = [Cr %] + 3.3 [Mo %] + 16 [N %] ≥ 24					



SANDMEYER STEEL COMPANY

ONE SANDMEYER LANE • PHILADELPHIA, PA 19116-3598
800-523-3663 • +1-215-464-7100 • FAX +1-215-677-1430

www.SandmeyerSteel.com

Providing Solutions, With Materials and Value Added Products, for Process Industries

Mechanical Properties

Tensile Properties (Minimum Values)

°C	Rp 0.2 MPa	Rp 1.0 MPa	Rm MPa	°F	YS 0.2% Offset KSI	YS 0.1% Offset KSI	UTS KSI	Elongation %
20	400	440	600	68	58	64	87	25
100	330	365	570	212	48	53	83	25
200	280	310	530	392	41	45	77	20
300	230	260	490	572	33	38	71	20

Values obtained for hot rolled plates ($th \leq 2''$). Alloy 2304 must not be used for a long time at temperatures higher than 300°C (572°F), where precipitation hardening phenomenon occurs.

Toughness Values (KCV Minimum Values)

Temp.	-50°C	+20°C	-60°F	+70°F
Single	75 J/cm ₂	90 J/cm ₂	54 ft. lbs	65 ft. lbs
Average (5)	90 J/cm ₂	150 J/cm ₂	65 ft. lbs	87 ft. lbs

Hardness (Typical Values)

Average (5)	HV ₁₀ 180-230	HB : 180-230	HRC _ 20
-------------	--------------------------	--------------	----------

Physical Properties

Density : 7,800 kg/m³ - 0.28 lb/in³

Interval Temper °C	Thermal expansion ax10 ⁻⁶ K ⁻¹	°C	Resistivity (μ ₂ cm)	Thermal conductivity (W.m ⁻¹ .K ⁻¹)	Specific heat (J.kg ⁻¹ .K ⁻¹)	Young modulus E (GPa)	Shear modulus G (GPa)
20-100	13	20	80	17	450	200	75
20-100	13	100	92	18	500	190	73
20-200	13.5	200	100	19	530	180	70
20-300	14	300	105	20	560	170	67

Structure

The chemical analysis of 2304 is optimized to obtain a typical 50 α / 50 γ microstructure after solution annealing treatment at 950°/1050°C (1742°/1922°F).

The microstructure of 2304 duplex is very stable compared to molybdenum containing duplex stainless steels. Intermetallic phases are present only after 10 hours holding time in the 750°/850°C (1382°/1562°F) temperature range. Copper additions to 2304 grade, when specified, increase the hardness of the steel after heat treatment in the 350°/500°C (662°/932°F) temperature range.

Processing

Hot Forming

Hot forming must be performed in the 1150°/900°C (2100°/1650°F) temperature range.

After forming, a new solution annealing treatment is recommended in the 950°/1050°C (2100°/1650°F) temperature range to fully restore corrosion resistance properties and mechanical properties. Parts formed with 2304 must be supported carefully during heating to avoid creep deformation.

Cold Forming

Alloy 2304 may be cold formed without any problem. The same equipment as used for the cold forming of 304L and 316L grades can be used. Due to its higher mechanical properties, including the yield strength, higher stresses are required for cold forming. A final solution annealing heat treatment is also recommended after cold forming in order to restore the mechanical and corrosion resistance properties, as described in 'hot forming.'


Descaling

Use the same solutions and pastes as for 304L/316L grades. The pickling time will be higher than for austenitic grades due to the corrosion resistance properties of the alloy.

Machinability

Alloy 2304 duplex exhibits improved machinability properties particularly when considering drilling. Its behavior is equivalent to that of 316LEZ*. Furthermore, 2304 has better corrosion resistance and cleanliness properties as no sulphur additions are necessary. Localized corrosion resistance behavior is improved.

*316LEZ is a 316L type grade with improved machinability properties.



Total length (drilling) versus drilling speed

Welding

- Alloy 2304 can be successfully welded by the following processes :
 - > TIG, manual and automatic
 - > PLASMA, MIG, SMAW, SAW, FCAW
- The duplex microstructure renders the alloy less sensitive to hot cracking.
- The welding parameters must be optimized to obtain a controlled ferrite level (20-70%). Typical recommended heat inputs are 10-25 KJ/cm with a 150°C (302°F) max interpass temperature. These conditions must be optimized taking into account the thickness of the products and welding equipment (consult if necessary). We do not recommend pre- or post-welding heat treatments. Only complete solution annealing heat treatment may be considered.

The information and data in this product data sheet are accurate to the best of our knowledge and belief, but are intended for informational purposes only, and may be revised at any time without notice. Applications suggested for the materials are described only to help readers make their own evaluations and decisions, and are neither guarantees nor to be construed as express or implied warranties of suitability for these or other applications.



**SANDMEYER
STEEL COMPANY**